



# Product Data Sheet

## Transvinyl Tar 2.05

### Product description.

A quick drying vinyl tar primer pigmented with aluminium flakes to enhance the water resistance properties. The product can be used as an anticorrosive system on itself or as a tiecoat on Transpoxy systems to improve the adhesion of subsequent antifouling systems.

### Physical properties.

Colour/Texture	Silvergrey and Silver brown/Semi-gloss
Volume Solids	42%
Specific gravity	1.1 gr/ml
Flashpoint	>14°C

	Dry film thickness per coat (μ)	Wet film thickness per coat (μ)	Theoretical spreading rate (m <sup>2</sup> /l)
Range	50 – 80	120 – 190	8.4 – 5.3
Recommended	75	180	5.6

### Application data.

<u>Guiding data Airless spray</u>	Pressure at nozzle: 120 -180 bar. Nozzle size: 0.38 - 0.53 mm. Spray angle: 40 - 80 degrees. Volume of thinner: 0 - 3%.
<u>Guiding data Airspray</u>	Pressure. 3 - 5 bar. Nozzle size: 1.2 - 2.0 mm. Volume of thinner: 0 - 10%.
<u>Brush/Roller</u>	Suitable. Multicoats are required to achieve the specified dry film thickness. Volume of thinner: 0 - 5%.
<u>Thinner/Cleaner</u>	Transocean Vinyl Thinner 6.05.
<u>Conditions</u>	Humidity: below 90% RH. Temperature of the paint before application: min: 10°C, max: 30°C. Substrate temperature: min: 1°C, max: 35°C. The temperature of the substrate should be at least 3°C above the dew point of the air. Air temperatures and relative humidity must be measured in the vicinity of the substrate.

### Drying and recoating times.

Substrate temperature	Touch dry	Hard dry	Dry to recoat	
			Minimum	Maximum (1)
10 °C	1 hour	2 days	12hours	Indefinite
23 °C	30 minutes	1 day	8 hours	Indefinite
30 °C	20 minutes	1 day	6 hours	Indefinite

(1) The surface should be dry and free from contaminants prior to overcoating. After prolonged exposure times it may be necessary to roughen the surface to ensure intercoat adhesion. When in doubt, consult your nearest Transocean office.

## Surface preparation.

Steel	Oil and grease should be removed by solvent cleaning according to SSPC-SP1. Remove weld spatter and smooth weld seams and sharp edges as applicable. Abrasive blasting: min. Sa2,5 – ISO 8501:1. Apply Transvinyl Tar 2.05 immediately after the steel has been blasted and the quality of preparation has been approved. Transvinyl Tar may also be applied on suitable Transpoxy primers such as Transoplate Epoxy Primer 1.57. Ensure that primed surfaces are dry and free from salts and other contaminants.
Repair	Corroded areas should be power tool cleaned to ISO-St3 or blast cleaned to ISO-Sa2 or better. Existing systems should be dry and free from loose paint, salt, grease and other contaminants prior to overcoating.

## Recommended paint system.

A typical system for immersion conditions is shown below.

Transvinyl Tar Silvergrey 2.05	1 x 75 µ dft.
Transvinyl Tar Silverbrown 2.05	1 x 75 µ dft.
Transvinyl Tar Silvergrey 2.05	1 x 75 µ dft.

Subsequent coating with suitable Transocean antifouling systems such as Transocean Longlife series.

## Health and safety.

Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety regulations should be followed. This product is intended for use by professional applicators.

As a general rule, avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spillage on the skin should immediately be removed by thorough washing with lukewarm water and soap or a suitable industrial cleaner. Eyes should be flushed with fresh water and medical attention sought immediately.

Spraying should be carried out under well-ventilated conditions. Avoid inhalation of solvent vapours and paint mist by wearing an air mask.

This product contains flammable materials and should be kept away from sparks and open flames.

Smoking in the area should not be permitted.

## Disclaimer

*The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factors affecting the use and application of this product.*

*Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product.*

*We reserve the right to change the product without notice.*

Date of issue: May 03