



Product Data Sheet

Transosil Finish 5.14

Product description.

Heat resistant finish based on acrylic silicone resins for installations where heat resistance up to 250 °C is required. The finish has good esthetical properties and is easy to apply.

Physical properties.

Colour/Texture	Silver, White/ Semi-gloss
Volume Solids	36%
Specific gravity	1.1 gr/ml
VOC	553 gr/liter
Flashpoint	>25°C

	Dry film thickness per coat (μ)	Wet film thickness per coat (μ)	Theoretical spreading rate (m ² /l)
Recommended	30	85	12.0

Application data.

<u>Guiding data Airless spray</u>	Pressure at nozzle: 120 –150 bar. Nozzle size: 0.22 - 0.38 mm. Spray angle: 40 - 80 degrees. Volume of thinner: Not advised
<u>Guiding data Air spray</u>	Pressure: 3 – 4 bar. Nozzle size: 1.2 - 1.5 mm. Volume of thinner: 0 – 5%.
<u>Brush/Roller</u>	Suitable. Volume of thinner: 0 – 5%.
<u>Thinner/Cleaner</u>	Transocean Special Thinner 6.01.
<u>Conditions</u>	Humidity: below 90% RH. Temperature of the paint before application: min: 10°C, max: 30°C. Substrate temperature: min: 1°C, max: 40°C. The temperature of the substrate should be at least 3°C above the dew point of the air. Air temperatures and relative humidity must be measured in the vicinity of the substrate.

Drying and recoating times.

Substrate temperature	Touch dry	Hard dry	Dry to recoat	
			Minimum	Maximum (1)
23 °C	1 hour	24 hours.	4 hours	Indefinite
30 °C	35 minutes	16 hours.	4 hours	Indefinite

(1) The surface should be dry and free from salts and other contaminants prior to overcoating. When in doubt, consult your nearest Transocean office.

Surface preparation.

Steel	Oil and grease should be removed by solvent cleaning according to SSPC-SP1. Remove weld spatter and smooth weld seams and sharp edges as applicable. Abrasive blasting: min. Sa2,5 – ISO 8501:1. Apply Transosil Finish immediately after the steel has been blasted and the quality of preparation has been approved.
Repair	The surface must be dry and free salts, grease and other contaminants prior to overcoating. Remove any salts and dirt by fresh water washing. Corroded areas should be power tool cleaned to ISO-St2 or blast cleaned to ISO-Sa2 or better.

Recommended paint system.

A typical anticorrosive system for industrial installations is shown below.

Transozinc Silicate Solventborne 1.52	1 x 75 µ dft.
Transosil Finish 5.14	1 x 30 µ dft.

Health and safety.

Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety regulations should be followed. This product is intended for use by professional applicators.

As a general rule, avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spillage on the skin should immediately be removed by thorough washing with lukewarm water and soap or a suitable industrial cleaner. Eyes should be flushed with fresh water and medical attention sought immediately.

Spraying should be carried out under well-ventilated conditions. Avoid inhalation of solvent vapours and paint mist by wearing an air mask.

This product contains flammable materials and should be kept away from sparks and open flames.

Smoking in the area should not be permitted.

Disclaimer

The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factors affecting the use and application of this product.

Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product.

We reserve the right to change the product without notice.

Date of issue: November, 12.