

NATIONALTHANE QUICK DRY
DECORATIVE COATINGS

TECHNICAL DATA SHEET

NATIONALTHANE QUICK DRY

PRODUCT DESCRIPTION	Two pack, colour retentive quick drying polyurethane topcoat, with excellent water, salt and corrosion resistance. The dry film is having excellent adhesion, flexibility and impact resistance on various surfaces. Due to its siperior U.V. resistance, it is recommended for interior and exterior
	applications, even in marine environment.

RECOMMENDED	- Topcoat for Epoxy system	
USES	- Topcoat on steel, wood and masonry	
	- Recommended as topcoat for extreme climatic conditions	

TECHNICAL DATA

COLOUR, DRY FILM	Clear	Colours
FINISH, DRY FILM	Glossy or Matt	Glossy or Matt
VOLUME SOLIDS	$33 \pm 2\%$	$38 \pm 2\%$
(ASTM D2697)		
SPECIFIC GRAVITY	0.95 ± 0.05 (Mixed)	1.15 ± 0.05 (Mixed)
THEORETICAL SPREADING	11 M ² /LTR	$9.5 \mathrm{M}^2/\mathrm{LTR}$
RECOMMENDED DFT (DRY	30 Microns/Coat	40 Microns/Coat
FILM)		
RECOMMENDED WFT (WET	90 Microns/Coat	105 Microns/Coat
FILM)		
FLASH POINT	18°C	18°C

DRYING TIME

Drying time @ 30 ℃ (Temperature, humidity, air movement, film thickness and number of coats	
all affect the drying time.)	
TOUCH DRY	20 – 30 minutes
DRY TO RECOAT	6 – 7 hours
FULLY CURED	2 – 3 days

ADVANTAGES

NATIONALTHANE QUICK DRY SYSTEM	Two pack, quick drying polyurethane, easy to apply, good coverage. Excellent adhesion to various surfaces, flexibility,
	impact resistance, superior U.V. resistance.



NATIONALTHANE QUICK DRY
DECORATIVE COATINGS

TECHNICAL DATA SHEET

APPLICATION INSTRUCTION

SURFACE PREPARATION	Before application, the surface should be sound, clean and free
	from oil, grease, loose particles, dust, etc. Application can be
	done by the recommended application methods.

APPLICATION DATA

APPLICATION METHOD	Brush, Roller or Spray
CLEANING/THINNING	National Polyurethane Thinner
THINNER (VOLUME)	5-15% depending on method of applications
CONV. SPRAY REQUIREMENTS	Possible
AIRLESS SPRAY	Pressure : 1500 – 2100 psi
REQUIREMENTS	
NOZZLE SIZE	0.016" – 0.019"
MIXING RATIO (BY VOLUME)	Base : Hardener
	4:1 (Mix properly before use)
POT LIFE @ 30°c (100 ml)	3 – 4 hours

SYSTEM

	National Polyurethane Primer	:	1 coat
RECOMMENDED SYSTEM To be applied on prepared surface.	(OR)		
	National Polyurethane Wood Sanding Sealer	:	1 coat
	Nationalthane Quick Dry	:	2 coats

ADDITIONAL DATA

SHELF LIFE @ 30°C	18 months, in original sealed container, with proper storage
	conditions.

HEALTH & SAFETY

SAFETY	As a general rule, avoid skin and eye contact by wearing
PRECAUTIONS	overalls, gloves, goggles, and mask etc. Spillage on skin should
	immediately be removed by thorough washing with water and
	soap or suitable cleaner. Eye should be flushed with fresh water.
	Avoid inhalation of vapours and paint mist by wearing suitable
	mask. In the event of ingestion and eye contact, seek medical
	attention immediately. Painting must be carried out in well-
	ventilated area.
	This product contains flammable materials and should be kept
	away from the sparks and open flames, smoking in the area
	should not be permitted. Local safety regulations should be
	followed.

Rev. 07/18 Page 2/3



NATIONALTHANE QUICK DRY DECORATIVE COATINGS

TECHNICAL DATA SHEET

STORAGE & HANDLING

STORAGE	Store the paint in proper storage conditions as per the local
	regulations. Keep the paint container in sealed condition under
	shed, away from direct sunlight and extreme temperatures. Do
	not stock paint material near to any ignition sources. Do not put
	back the half or unused material back in original container,
	containing the supplied paint, to avoid contamination. Handle
	with care. Stir well before use.

NOTE: We warranty only the quality of our product and this data sheet is based on results obtained from experience and tests. We reserve the right to change data without prior notice. For surface preparation, safety details refer specifier and safety data

This data sheet supersedes all previous issued.

Issued: 0718