



Product Data Sheet

Transolac Varnish 3.81

Product description.

A fast drying, urethane modified synthetic varnish for interior and exterior use. It has excellent flow properties and provides a brilliant appearance and an elastic coating film.

Physical properties.

Colour/Texture Transparent/Glossy
Volume Solids 47%
Specific gravity 0.91 gr/ml
Flashpoint >21°C

	Dry film thickness per coat (μ)	Wet film thickness per coat (μ)	Theoretical spreading rate (m ² /l)
Range	30 – 50	65 – 105	15.7 – 9.4
Recommended	35	75	13.4

Application data.

Brush/Roller Suitable.
Volume of thinner: 0 - 15%.

Thinner/Cleaner Transocean Standard Thinner 6.00.

Conditions Humidity: below 90% RH.
Temperature of the paint before application: min: 1°C, max: 30°C.
Substrate temperature: min: 5°C, max: 30°C.
The temperature of the substrate should be at least 3°C above the dew point of the air. Air temperatures and relative humidity must be measured in the vicinity of the substrate.

Drying and recoating times.

Substrate temperature	Touch dry	Hard dry	Dry to recoat	
			Minimum	Maximum (1)
10 °C	8 hours	16 hours	16 hours	Indefinite
23 °C	4 hours	8 hours	8 hours	Indefinite
30 °C	2 hours	6 hours	6 hours	Indefinite

(1) The surface should be dry and free from salts and other contaminants prior to overcoating. After prolonged exposure times it may be necessary to roughen the surface in order to ensure intercoat adhesion. When in doubt, consult your nearest Transocean office.

Surface preparation.

Tropical wood	It is advised to apply a suitable polyurethane clear varnish as a first coat in order to seal aggressive substances in the wood.
Other woods	The wood should be sanded to a smooth and even surface using silica paper or a sanding disc. Maximum allowable moisture content in soft-woods; 15%. Maximum allowable moisture content in leaf-woods; 12%.

Recommended paint system.

Transolac Varnish is normally applied in three or four coats. When coating porous wood qualities it is advised to thin down the first coat with 10% thinner. The following coats can be applied without thinner.

Health and safety.

Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety regulations should be followed. This product is intended for use by professional applicators.

As a general rule, avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spillage on the skin should immediately be removed by thorough washing with lukewarm water and soap or a suitable industrial cleaner. Eyes should be flushed with fresh water and medical attention sought immediately. Spraying should be carried out under well-ventilated conditions. Avoid inhalation of solvent vapours and paint mist by wearing an air mask.

This product contains flammable materials and should be kept away from sparks and open flames. Smoking in the area should not be permitted.

Disclaimer

The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factors affecting the use and application of this product.

Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product.

We reserve the right to change the product without notice.

Date of issue: January, 1999.