



NATIONAL ALUMINIUM H.T. 600°C
PROTECTIVE COATINGS

TECHNICAL DATA SHEET

NATIONAL ALUMINIUM H.T. 600°C

PRODUCT DESCRIPTION	A heat resistant modified silicon based aluminium paint for atmospheric exposure conditions, having good weather resistance. It has good flow and leveling and has heat resistance up to 600°C. It should preferably be applied by spray to get the best results. An initial minimum temperature of 200°C is required to initiate the cure of the film.
----------------------------	---

RECOMMENDED USES	A heat resisting paint for steel structure, pipes, power stations, high temperature stacks, boilers, engines, exhaust lines, etc. where heat resistance up to 600°C is required.
-------------------------	--

TECHNICAL DATA

COLOUR, DRY FILM	Aluminium
FINISH, DRY FILM	Metallic / Lustrous
VOLUME SOLIDS (ASTM D2697)	24 ± 2%
SPECIFIC GRAVITY	0.98 ± 0.05
THEORETICAL SPREADING RANGE	8 M ² /LTR
RECOMMENDED DFT RANGE (DRY FILM THICKNESS)	30 Microns/Coat
RECOMMENDED WFT RANGE (WET FILM THICKNESS)	125 Microns/Coat
FLASH POINT	28°C
FLEXIBILITY	Good
ABRASION RESISTANCE	Good
WEATHER RESISTANCE	Good

DRYING TIME

Drying time @ 30°C (Temperature, humidity, air movement, film thickness and number of coats all affect the drying time.)	
TOUCH DRY	1 hour
*DRY TO RECOAT / OVERCOAT	4 hours
FULLY CURED	1. The product cures by a gradual rise in temperature. The following cure schedule is recommended: <ul style="list-style-type: none"> - 30 minutes gradual rise to 100°C - 1 hour gradual rise to 200°C - 2 hour rise to 450°C

*With same generic type paint.



**NATIONAL ALUMINIUM H.T. 600°C
PROTECTIVE COATINGS**

TECHNICAL DATA SHEET

ADVANTAGES

NATIONAL ALUMINIUM H.T. 600°C	Single component aluminium paint. Dried film has excellent adhesion on metal surface, along with superior oil resistance and heat resistance up to 600°C.
--------------------------------------	---

APPLICATION INSTRUCTION

SURFACE PREPARATION	Surface is to be blast cleaned to Sa2.5 to obtain maximum heat resistance.
----------------------------	--

APPLICATION DATA

APPLICATION METHOD	Airless Spray	Conventional Spray	Brush
CLEANING/THINNING	National G.P. Thinner		
THINNER (VOLUME)	Ready to use		
CONV. SPRAY REQUIREMENTS	Atomizing Pressure : 40 psi		
AIRLESS SPRAY REQUIREMENTS	Pressure: 2200 psi		
NOZZLE SIZE	0.016" – 0.018"		
MIXING RATIO (BY VOLUME)	Not applicable		
POT LIFE @ 30°C (100 ml)	Not applicable		

SYSTEM

RECOMMENDED SYSTEM To be applied on prepared surface.	No. of Coats x DFT (Microns)	
	National Aluminium H.T. 600°C	: 2 x 30

ADDITIONAL DATA

SHELF LIFE @ 30°C	6 months, in original sealed container, with proper storage conditions.
--------------------------	---

HEALTH & SAFETY

SAFETY PRECAUTIONS	As a general rule, avoid skin and eye contact by wearing overalls, gloves, goggles, and airmask etc. Spillage on skin should immediately be removed by thorough washing with water and soap or suitable cleaner. Eye should be flushed with fresh water. Avoid inhalation of vapours and paint mist by wearing suitable airmask. In the event of ingestion and eye contact, seek medical attention immediately. Painting must be carried out in well-ventilated area. This as industrial product contains flammable materials and should be kept away from the sparks and open flames, smoking in the area should not be permitted. Local safety regulations should be followed.
---------------------------	--



**NATIONAL ALUMINIUM H.T. 600°C
PROTECTIVE COATINGS**

TECHNICAL DATA SHEET

STORAGE & HANDLING

STORAGE	Store the paint in proper storage conditions as per the local regulations. Keep the paint container in sealed condition under shed, away from direct sunlight and extreme temperatures. Do not stock paint material near to any ignition sources. Do not put back the half or unused material back in original container, containing the supplied paint, to avoid contamination. Handle with care. Stir well before use.
----------------	--

NOTE: We warranty only the quality of our product and this data sheet is based on results obtained from experience and tests. We reserve the right to change data without prior notice. For surface preparation, safety details refer specifier and safety data.

This data sheet supersedes all previous issued.
Issued: 0608