

NATIONALTHANE PEARL FINISH DECORATIVE COATINGS

TECHNICAL DATA SHEET

NATIONALTHANE PEARL FINISH

resistance to water, abrasion and marine environments, with excellent U.V. resistance. It has high gloss retention with elegant pearl appeal.

RECOMMENDED	As a topcoat for metal, cementitious and wooden surfaces.		
USES	Recommended for interior and exterior applications. Also		
	recommended on metal profiles and for maintenance jobs.		

TECHNICAL DATA

COLOUR, DRY FILM	As per National Shade Card
FINISH, DRY FILM	Smooth / Glossy / Pearlescent
VOLUME SOLIDS	$27 \pm 2\%$
(ASTM D2697)	
SPECIFIC GRAVITY	1.00 ± 0.05 (mixed)
THEORETICAL SPREADING	9 M ² /LTR
RECOMMENDED DFT (DRY	30 Microns/Coat
FILM)	
RECOMMENDED WFT (WET	110 Microns/Coat
FILM)	
FLASH POINT	25°C

DRYING TIME

Drying time @ 30 ℃ (Temperature, humidity, air movement, film thickness and number of coats			
all affect the drying time.)			
TOUCH DRY 3 – 5 hours			
DRY TO RECOAT	12 – 24 hours		
HARD DRY	48 hours		
FULLY CURED	2 – 3 days		

ADVANTAGES

NATIONALTHANE PEARL FINISH	Pearlescer	nt ef	fect, with	excellent	water	resista	nce,	cher	nical
SYSTEM	resistance	and	abrasion	resistance	. The	dried	film	is	also
	resistant to	high	impact.						



NATIONALTHANE PEARL FINISH DECORATIVE COATINGS

TECHNICAL DATA SHEET

APPLICATION INSTRUCTION

SURFACE PREPARATION	Before application, the surface should be sound, clean and free
	from oil, grease, loose particles, dust, etc. Application can be
	done by the recommended application methods.

APPLICATION DATA

APPLICATION METHOD	Conventional spray, Airless Spray, roller.
CLEANING/THINNING	National Polyurethane Thinner
THINNER (VOLUME)	5%, depending on method of application
CONV. SPRAY REQUIREMENTS	Pressure: 50 psi
AIRLESS SPRAY	Pressure : 2200 psi
REQUIREMENTS	
NOZZLE SIZE	0.016" – 0.019"
MIXING RATIO (BY VOLUME)	Base : Hardener
	4:1 (Mix properly keep for 10-15 minutes before use)
POT LIFE @ 30°c (100 ml)	8 hours

SYSTEM

	For Metal and Cementitious surfaces:		
To be applied on prepared surface.	National Polyurethane Primer	:	1 coat
	Nationalthane Pearl Finish	:	1 coat
	For more glossy effect apply:		
	Nationalthane Varnish	:	1 coat
	OR		
	Other National recommended system.		

ADDITIONAL DATA

SHELF LIFE @ 30°C	6 months, in original sealed container, with proper storage
	conditions.



NATIONALTHANE PEARL FINISH DECORATIVE COATINGS

TECHNICAL DATA SHEET

HEALTH & SAFETY

SAFETY	As a general rule, avoid skin and eye contact by wearing
PRECAUTIONS	overalls, gloves, goggles, and mask etc. Spillage on skin should
	immediately be removed by thorough washing with water and
	soap or suitable cleaner. Eye should be flushed with fresh
	water. Avoid inhalation of vapours and paint mist by wearing
	suitable mask. In the event of ingestion and eye contact, seek
	medical attention immediately. Painting must be carried out in
	well-ventilated area.
	This product contains flammable materials and should be kept
	away from the sparks and open flames, smoking in the area
	should not be permitted. Local safety regulations should be
	followed.

STORAGE & HANDLING

STORAGE	Store the paint in proper storage conditions as per the local
	regulations. Keep the paint container in sealed condition under
	shed, away from direct sunlight and extreme temperatures. Do
	not stock paint material near to any ignition sources. Do not put
	back the half or unused material back in original container,
	containing the supplied paint, to avoid contamination. Handle
	with care. Stir well before use.

NOTE: We warranty only the quality of our product and this data sheet is based on results obtained from experience and tests. We reserve the right to change data without prior notice. For surface preparation, safety details refer specifier and safety data.

This data sheet supersedes all previous issued.

Issued: 0718